



## TEST REPORT

|                |                      |                         |                   |
|----------------|----------------------|-------------------------|-------------------|
| <b>CLIENT:</b> | X-Grass              | <b>REPORT NUMBER:</b>   | 51006-01          |
|                | PO Box 579           | <b>LAB TEST NUMBER:</b> | 2298-7303         |
|                | Rocky Face, GA 30740 | <b>DATE:</b>            | February 24, 2011 |

**TURF ID:**

|                       |
|-----------------------|
| <b>Identification</b> |
| Bonded Rubber         |

**Subject:** Testing Services Inc was instructed by the client to determine the flammability of bonded rubber pour in place material when exposed to an ignition source under controlled laboratory conditions.

**Test Method:** *ASTM D-2859: Standard Test Method for Flammability of Finished Textile Floor Covering Materials*

*Code of Federal Regulations: 16 CFR 1631 (FF2-70) < 6ft & 24 ft<sup>2</sup>*

*Code of Federal Regulations: 16 CFR 1630 (FF1-70) > 6ft & 24 ft<sup>2</sup>*

**Test Scope:** This test method is part of the standards for the surface flammability of carpets and rugs of the U.S. Consumer Product Safety Commission. The acceptance criteria of this standard calls for the charred portion of at least seven out of eight individual specimens not extend to within 1" of the steel frame placed on top of the sample when exposed to a centrally placed methenamine pill tablet.

**Test Data:**

| Specimen Number | Un-charred Area |
|-----------------|-----------------|
| 01              | 0               |
| 02              | > 2"            |
| 03              | > 3"            |
| 04              | > 3"            |
| 05              | > 3"            |
| 06              | > 3"            |
| 07              | > 3"            |
| 08              | > 2"            |

**Test Summary**

| Pass | Failure | Status |
|------|---------|--------|
| 7    | 1       | Passes |

Approved By:

\_\_\_\_\_  
 Erle Miles Jr. VP  
 Testing Services Inc.